

GENERAL PURPOSE SERIES

TECPLEX® 2460M5 is a calcium sulfonate grease fortified with 5% molybdenum disulfide, developed specifically for use in the most extreme Steel Mill applications. The product is formulated to withstand intense heat while providing excellent protection from extreme pressures of working with heavy loads in steel processing. The addition of the moly-based solid lubricant provides an extra layer of protection for equipment that can be prone to seizing due to rapid temperature changes (ladles) or extreme pressures (coiler mandrels).



TYPICAL APPLICATIONS

- Ladle Turrets
- Coiler Mandrels

KEY FEATURES

- Grade 2, ISO 460 Formulation.
- Moly-fortified formulation = Maximum protection from extreme pressures resulting from shock loads
- Superior protection from rust and corrosion
- Excellent resistance to water washout
- Outstanding high-temperature properties
- Environmentally friendly since the formulation contains no antimony, barium, chlorine, phosphorus, zinc or free sulfur







GENERAL PURPOSE SERIES

PHYSICAL PROPERTIES	TEST METHOD	TYPICAL VALUES
NLGI Grade	ASTM D217	2
Color	Visual	Gray
Texture	Visual	Smooth
Dropping Point, °C	ASTM D2265	316°C +
Worked Penetration, 60 Double Strokes, dmm	ASTM D217	265 - 295
Mechanical Stability		
Worked Penetration 10,000 Double Strokes,	ASTM D217	< 3.0
% Change		₹ 3.0
Worked Penetration 10,000 Double Strokes 10% Water,	ASTM D217	< 3.0
% Change		
Roll Stability, % change	ASTM D1831	< 3.0
Timken OK Load, kg	ASTM D2509	27.2
4-Ball EP: LWI, kgf	ASTM D2596	60
Weld Point, kg	ASTM D2596	500
4-Ball Wear, mm	ASTM D2266	0.60
Fretting Wear, mg	ASTM D4170	<10.0 mg
Bearing Rust Protection	ASTM D1743	Pass
Salt Fog Corrosion, 1 mil d.f.t., hours	ASTM B117	>500
Wheel Bearing Leakage, grams	ASTM D4290	< 3
Bearing Life Performance, hours Bomb Oxidation, 100 hours @ 99°C, PSI Drop	ASTM D3527 ASTM D942	100+ < 1
Water Washout, % removed	ASTM D942 ASTM D1264	<1
Water Spray Off, % removed	ASTM D4049	10.4
Oil Separation, % loss	ASTM D1742	<0.5
Copper Strip Corrosion	ASTM D4048	1b
Elastomer Compatibility	ASTM D4040 ASTM D4289	10
AMS 3217 / 3B CR Type 70 hours @ 100°C	7.01W B-1200	
Percent Swell		+6.6
Hardness Change, Durometer A points		-3.5
AMS 3217 / 2B NBR-L Type 70 hours @ 150°C		
Percent Swell		+1.8
Hardness Change, Durometer A points		-1.3
Base Oil Viscosity, cSt	ASTM D445	
@ 100°C		30.6
@ 40°C		460
Viscosity Index		97.5
Emcor Corrosion, 3% NaCl	ASTM D6138	2,2

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

WARRANTY: Coast Lubricants and Industrial Supply warrants all products manufactured by it to be free from defects in material and workmanship. COAST LUBRICANTS AND INDUSTRIAL SUPPLY MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILTY AND FITNESS FOR PARTICULAR PURPOSE AND IMPLIED WARRANTIES OF MERCHANTABILTY AND FITNESS FOR PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY COAST LUBRICANTS AND INDUSTRIAL SUPPLY. AII INPLIED WARRANT INSENTATION A COURSE OF DEALINGS OF VIOLAGE OF IT AND CARGED FOR THE ARE DISCLAFFED BY COAST LUMBER AND INDUSTRIAL SUPPLY. AND CHARGE OF ITAMIC, ARE DISCLAFFED BY AND AND CARGED OF ITAMIC AND CARGED OF I sale or use of its products.

DUVCIONI DDODEDTICO

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

TYDICAL VALUE

